



DESCRIPTION

Modified polyurethane alkyd containing solvent based exterior impregnated varnish.

FEATURES

It protects the wooden surfaces from external factors like rain and moisture thanks to its special additive mixtures reinforced binder structure and anti-pest content. Dr.Wood Decorative Wood Stain is colored with clear iron-oxide pigments and it gives a natural look and protection to the wooden surfaces. It doesn't contain high coloring capacity.

RECOMMENDED APPLICATION FIELDS

Can be applied safely on every kind of wooden surfaces, doors, windows, outdoor furnitures, pergolas etc.

CHARACTERISTICS

<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">PAINT FILM</td> <td>Transparent- Check wood stain catalog</td> </tr> <tr> <td>BINDER TYPE</td> <td>Urethane Alkyd</td> </tr> <tr> <td>VISCOSITY</td> <td>15-20 sn DIN CUP 4</td> </tr> <tr> <td>SPECIFIC GRAVITY</td> <td>0,81-0,83 kg/ltr</td> </tr> <tr> <td>SOLID CONTENT(%By Weight)</td> <td>20-22</td> </tr> <tr> <td>V.O.C</td> <td>Max. 590 gr/L</td> </tr> </table> <p>RECOMMENDED FILM THICKNESS</p> <p>When applied as 20 µ dry film thickness it is possible to paint 12-14 m² area with 1 lt of varnish. Note: Application area may differ based on application conditions.</p> <p>CLEANING METHOD OF APPLICATION Synthetic Thinner, Thinner 646</p> <p>SHELF LIFE 24 months unopened original box</p> <p>STORAGE TEMPERATURE It is best suited for indoors with no direct sunlight between 5 ° C and 35 ° C.</p>	PAINT FILM	Transparent- Check wood stain catalog	BINDER TYPE	Urethane Alkyd	VISCOSITY	15-20 sn DIN CUP 4	SPECIFIC GRAVITY	0,81-0,83 kg/ltr	SOLID CONTENT(%By Weight)	20-22	V.O.C	Max. 590 gr/L	<table style="width: 100%; border-collapse: collapse;"> <tr> <th colspan="2" style="text-align: center;">AVERAGE DRYING TIMES</th> </tr> <tr> <td></td> <td style="text-align: center;">25°C %40-70 Relative humidity</td> </tr> <tr> <td>Hard Dry</td> <td style="text-align: center;">24 hours</td> </tr> <tr> <td>Time between layers</td> <td style="text-align: center;">12 hours</td> </tr> </table> <p>Drying times can be change on temperature, relative humidity and film thickness</p>	AVERAGE DRYING TIMES			25°C %40-70 Relative humidity	Hard Dry	24 hours	Time between layers	12 hours
PAINT FILM	Transparent- Check wood stain catalog																				
BINDER TYPE	Urethane Alkyd																				
VISCOSITY	15-20 sn DIN CUP 4																				
SPECIFIC GRAVITY	0,81-0,83 kg/ltr																				
SOLID CONTENT(%By Weight)	20-22																				
V.O.C	Max. 590 gr/L																				
AVERAGE DRYING TIMES																					
	25°C %40-70 Relative humidity																				
Hard Dry	24 hours																				
Time between layers	12 hours																				

SURFACE PREPARATION

Can be applied by roller, brush or cloth. Make sure that the surface is clean, dry and free from materials that might block the adhesion (wax, wood resin, mold). Stir well before using. Apply 2 coats. If needed, to obtain a lighter color shade, dilute by using synthetic thinner. Do not apply on surfaces containing more than 18% moisture.

APPLICATION	APPLICATION CONDITIONS
-------------	------------------------

<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">Application Method</td> <td>Brush</td> </tr> <tr> <td>Brush Type</td> <td>Naylon/polyesther or natural hair brush</td> </tr> <tr> <td>Thinning</td> <td>Ready to use- If needed Synthetic Thinner ,white spirit, Stoddart Solvent, Thinner 650</td> </tr> <tr> <td>Wet Film Thickness</td> <td>100 micron</td> </tr> <tr> <td>Dry Film Thickness</td> <td>20 micron</td> </tr> <tr> <td>Waiting Time Between Layers</td> <td>min 12 hours at 25 ° C , 16 hours at 10 ° C</td> </tr> </table>	Application Method	Brush	Brush Type	Naylon/polyesther or natural hair brush	Thinning	Ready to use- If needed Synthetic Thinner ,white spirit, Stoddart Solvent, Thinner 650	Wet Film Thickness	100 micron	Dry Film Thickness	20 micron	Waiting Time Between Layers	min 12 hours at 25 ° C , 16 hours at 10 ° C	<p>Temperature (air, surface, Product): 15 ° C minimum, 35 ° C maximum At least 3 ° C above dew point Relative Humidity: 85% maximum</p>
Application Method	Brush												
Brush Type	Naylon/polyesther or natural hair brush												
Thinning	Ready to use- If needed Synthetic Thinner ,white spirit, Stoddart Solvent, Thinner 650												
Wet Film Thickness	100 micron												
Dry Film Thickness	20 micron												
Waiting Time Between Layers	min 12 hours at 25 ° C , 16 hours at 10 ° C												
CERTIFICATES / APPROVALS													
ADDITIONAL INFORMATION													

RECOMMENDED SYSTEMS	HEALTH AND SAFETY
---------------------	-------------------

	<p>Read the Safety Data Sheet before use. CST reserves the right to change technical document. Contact our technical service department for more information.</p>
WARRANTY	
<p>CST guarantees that this product is manufactured in accordance with standards and without any error. In the event of a proven manufacturing defect, CST will replace the defective product or refund the fee. Under certain circumstances, CST does not provide warranties.</p>	

Disclaimer

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of CST Kimya A.Ş. Their accuracy, completeness or appropriateness for the actual conditions of any intended use of the products herein must be determined exclusively by the Buyer and/or User. Product information are provided "as is" and to the extent permitted by law, without any kind of guarantee, commitment or liability. Except in case of willful misconduct, CST Kimya A.Ş is not liable for damages that are caused by or in connection with the use of the information. In any case, CST Kimya A.Ş is not responsible for and assumes no liability for any indirect, incidental or consequential damages that are caused by or in connection with the use of the information.



its.
lead and



s.



only as 2



change the
r more



with the
cturing
rder no



ness under
mitted by
e of this
se of such